

TECHNICAL INFORMATION

PRODUCT : PL : WOOD FREE PAPER LABEL

WFWHOM70/PE-18/KRYEOM75

SURFACE	WFWHOM70
---------	----------

Type	Matt White Wood free paper	
<u>PHYSICAL PROPERTIES</u>		<u>GENERAL CHARACTERISTIC</u>
Basic Weight	70 ± 5 g / m ²	1. Suitable for general print application
Thickness	0.085 ± 0.005 mm.	2. Application where matted white paper.

ADHESIVE	PE-18
----------	-------

Type	Acrylic Emulsion	
<u>PROPERTIES</u>		<u>GENERAL CHARACTERISTIC</u>
Adhesion (S/Steel)	≥ 1.8 kg.f / 25 mm	1. Permanent type which high Initial tack and high peel adhesion.
Loop Tack	3.5 ± 0.7 psi.	
End user temperature	min. - 5 °C max. + 80 °C	2. Good adhesion to metal, plastic, paper, and glass etc.
Providing range	min -20 °C	
Shelf life	1 year under optimum storage condition	3. The adhesive complies with FDA 175.105 and approved for indirect contact food.

LINER	KRYEOM75
-------	----------

Type	PE Kraft Release Liner
------	------------------------

<u>PROPERTIES</u>	
Basic Weight	90 ± 5 g/m ²
Thickness	0.110 ± 0.010 mm.
Color	Light Yellow

APPLICATION

For General product labeling applications which good printability and suitable for all high volume tag etc. price tag, instruction label, address, hospital.

CAUTION

1. All technical data statements are typical and should not be used for specification purpose.
2. The Product must be stored in shady (or cool) place and do not expose to sunlight directly.
3. Before using, user shall determine the suitability of the product for their intended use.

Note : 1. Peel adhesion and Loop tack value are measured by ASTM and JIS test method ones under control condition (23 ± 2,65 ± 5%) and not guaranteed.

2. Substrates to be applied and methods of application may be distinguishable. You may contact us for more details through Technical Development Staff at technical@thaikk.co.th or call number 662-7083817